



# TEST REPORT



1. NO : CT26-002414E
2. Client
  - Name : Saint-Gobain Isover Korea
  - Address : 70, Bugokgongdan 1-gil, Songak-eup, Dangjin-si, Chungcheongnam-do, Korea
3. Date of Test : 2026.01.08 ~ 2026.03.12
4. Use of Report : Quality Control
5. Test Sample : Weatherproof 32[40K]
6. Test Method
  - (1) KS L 9102:2014

## 7. Test Results

### 1) Weatherproof 32[40K]

Test Item(s)	Unit	Test Method	Test Results	Remark	Loc.
density	kg/m <sup>3</sup>	(1)	41	-	A
Thermal Shrinkage	℃	(1)	405		
Thermal Conductivity[Mean temperature : 20 ℃]	W/(m·K)	(1)	0.032		
Thermal Conductivity[Mean temperature : 70 ℃]	W/(m·K)	(1)	0.038		

※ Specimen Thickness : 50 mm

※ Location

A : 73, Yangcheong 3-gil, Ochang-eup, Cheongwon-gu, Cheongju-si, Chungcheongbuk-do, Republic of Korea

----- End of Report -----

Affirmation	Tested By	<i>Lim Soon Hyun</i>	Technical Manager	<i>Geo Jun Sik</i>
	Name : Soon Hyun, Lim		Name : JUN SIK SEO	

This report is related with KOLAS and KS Q ISO/IEC 17025.

Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The results of using only a portion of this report cannot be guaranteed. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).

The above test report provides test result(s) under the scope accredited by Korea Laboratory Accreditation Scheme (KOLAS), which signed the ILAC-MRA.

2026.03.12

**Korea Conformity Laboratories**

Accredited by KOLAS, Republic of KOREA



Result Inquiry : 73, Yangcheong 3-gil, Ochang-eup, Cheongwon-gu, Cheongju-si, Chungcheongbuk-do, Republic of Korea  
82-43-210-8932

